

Material: DIN NiCo20Cr20MoTi

Standard Specification for Nickel, Molybdenum and Chromium Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiCo20Cr20MoTi Nickel, Molybdenum and Chromium Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.080	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 max.		
Chromium	Cr %	19.000 - 21.000		
Aluminium	Al %	0.300 - 0.600		
Al + Ti	Al % + Ti %	2.400 - 2.800		
Boron	B %	0.005 max.		
Cobalt	Co %	19.000 - 21.000		
Copper	Cu %	0.200 max.		
Iron	Fe %	0.700 max.		
Molybdenum	Mo %	5.600 - 6.100	Mechanical Properties	
Phosphorus	P %	0.020 max.	Tensile Strength in Mpa	540 min.
Sulphur	S %	0.015 max.	Yield Strength in Mpa	400 min.
Titanium	Ti %	1.900 - 2.400	Elongation in %	12 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
			Hardness in HB	230 - 250
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4650	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com