

Material: DIN NiCr20Mo15

Standard Specification for Nickel and Nickel Alloy Forgings

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiCr20Mo15 Nickel and Nickel Alloy Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Forging

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.050 max.
Manganese	Mn %	0.800 max.
Chromium	Cr %	19.000 - 21.000
Cobalt	Co %	2.500 max.
Iron	Fe %	2.500 max.
Copper	Cu %	0.500 max.
Molybdenum	Mo %	14.000 - 17.000
Phosphorus	P %	0.030 max.
Sulphur	S %	0.015 max.
Vanadium	V %	0.350 max.
Nickel	Ni %	58.000 min.
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	700 min.
Yield Strength in Mpa	310 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in HB	260 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4811	DIN	Germany	Forging
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India