

Material: DIN NiCr23Fe

Standard Specification for Nickel and Chromium Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiCr23Fe Nickel and Chromium Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	21.000 - 25.000		
Copper	Cu %	0.500 max.		
Cobalt	Co %	1.500 max.		
Aluminium	Al %	1.000 - 1.700		
Boron	B %	0.006 max.		
Iron	Fe %	18.000 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.	Mechanical Properties	
Titanium	Ti %	0.500 max.	Tensile Strength in Mpa	550 - 750
Nickel	Ni %	58.000 - 63.000	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	220 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4851	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com