

Material: DIN NiCr25FeAlYC

Standard Specification for Nickel and Chromium Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiCr25FeAlYC Nickel and Chromium Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.400	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.100 max.		
Chromium	Cr %	24.000 - 26.000		
Aluminium	Al %	2.400 - 3.000		
Copper	Cu %	0.150 max.		
Iron	Fe %	8.000 - 11.000		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Titanium	Ti %	0.100 - 0.250		
			Mechanical Properties	
Yttrium	Y %	0.050 - 0.150	Tensile Strength in Mpa	680 min.
Zirconium	Zr %	0.010 - 0.100	Yield Strength in Mpa	270 min.
Nickel	Ni %	Balance	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	220 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4647	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com