

Material: DIN NiCr2MnSi

Standard Specification for Nickel and Nickel Alloys Wires

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiCr2MnSi Nickel and Nickel Alloys Wires

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Wire

Chemical Composition		
Carbon	C %	0.050 max.
Silicon	Si %	0.400 - 0.650
Manganese	Mn %	1.300 - 1.800
Copper	Cu %	0.150 max.
Iron	Fe %	0.300 max.
Chromium	Cr %	1.400 - 1.800
sulphur	S %	0.005 max.
Titanium	Ti %	0.100 max.
Ni + Co	Ni% + Co%	95.500 min.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As-Cast or Annealing or Age Hardning	

Mechanical Properties	
Tensile Strength in Mpa	400 min.
Yield Strength in Mpa	140 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4146	DIN	Germany	Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com