

Material: DIN NiMo16Cr15W

Standard Specification for Nickel and Nickel Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiMo16Cr15W Nickel and Nickel Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.500 - 16.500		
Cobalt	Co %	2.500 max.		
Iron	Fe %	4.000 - 7.000		
Molybdenum	Mo %	15.000 - 17.000		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.010 max.	Mechanical Properties	
Vanadium	V %	0.350 max.	Tensile Strength in Mpa	690 min.
Tungsten	W %	3.000 - 4.500	Yield Strength in Mpa	280 min.
Nickel	Ni %	Balance	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	240 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4819	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com