

Material: DIN X 8 CrNiMoVNb 16 13

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: DIN X 8 CrNiMoVNb 16 13 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Tube

Chemical Composition		
Carbon	C %	0.040 - 0.100
Silicon	Si %	0.300 - 0.600
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	15.500 - 17.500
Molybdenum	Mo %	1.100 - 1.500
Nickel	Ni %	12.500 - 14.500
Vanadium	V %	0.600 - 0.850
Niobium	Nb %	1.200 max.
Nitrogen	N %	0.060 - 0.140
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	540 - 740
Yield Strength in Mpa	255 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4988	BS	British	Tube
1.4988	DIN	Germany	Steel
1.4988	EN	European Union	Steel
X8CrNiMoVNb16-13	EN	European Union	Steel and Flat
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India