

# Material: DIN X2CrNiMoN25-7-4

## Standard Specification for Seamless Steel Tubes for Pressure Purposes

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** DIN X2CrNiMoN25-7-4 Seamless Steel Tubes for Pressure Purposes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Steel, Strip, Plate and Sheet

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	24.000 - 26.000
Molybdenum	Mo %	3.000 - 4.500
Nickel	Ni %	6.000 - 8.000
Nitrogen	N %	0.200 - 0.350
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	730 - 2100
Yield Strength in Mpa	500 min.
Elongation in %	15 min.
Reduction of Area in %	-
Hardness in HB	310 max.
Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4410	BS	British	Tube
1.441	EN	European Union	Steel, Sheet, Plate and Strip
1.441	DIN	Germany	Steel, Sheet, Plate and Strip
X2CrNiMoN25-7-4	AFNOR NF	France	Steel
X2CrNiMoN25-7-4	UNI	Italy	Steel, Bar and Rod
X2CrNiMoN25 7 4	EN	European Union	Steel and Forging
S32750	UNS	USA	Steel

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India