

Material: DIN ZP0010

Standard Specification For Zinc and Zinc Alloy Castings

Group: Non-Ferrous Zinc Alloys

Sub Group: DIN ZP0010 Zinc and Zinc Alloy Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 - 0.040	As-Cast	
Copper	Cu %	1.000 - 1.500		
Magnesium	Mg %	0.020 max.		
Chromium	Cr %	0.100 - 0.200		
Titanium	Ti %	0.150 - 0.250		
Lead	Pb %	0.005 max.		
Cadmium	Cd %	0.005 max.		
Tin	Sn %	0.004 max.		
Iron	Fe %	0.050 max.		
Silicon	Si %	0.050 max.		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 220 min. Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP16	DIN	Germany	Casting
ZP16	UNI	Italy	Casting
ZP16	BS	British	Casting
ZP0010	UNE	Spain	Casting
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com