

Material: EN 10083-3 1.7182

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: EN 10083-3 1.7182 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.240 - 0.300	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	1.100 - 1.140		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.300 - 0.600		
Boron	B %	0.0008 - 0.0050		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	800 - 100
-	-	-	Yield Strength in Mpa	700 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	As Per HT
-	-	-	Impact in Joule	65 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
27MnCrB5-2	EN	European Union	Bar and Rod
27MnCrB5-2	ISO	International	Bar and Rod
1.7182	DIN	Germany	Bar and Rod
27MnCrB5-2	DIN	Germany	Bar and Rod
1.7182	SFS	Finland	Bar and Rod
27MnCrB5-2	SFS	Finland	Bar and Rod
1.7182	CSN	Czech Republic	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com