

Material: EN 10083-3 20MnB5

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: EN 10083-3 20MnB5 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	1.100 - 1.400		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.035 max.		
Boron	B %	0.0008 - 0.0050		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 750 - 900 Yield Strength in Mpa 600 min. Elongation in % 15 min. Reduction of Area in % - Hardness in BHN As Per HT Impact in Joule 60 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.5530	EN	European Union	Bar and Rod
20 MB 5	AFNOR NF	France	Bar, Wire and Rod
20MnB5	ISO	International	Bar and Rod
1.553	UNI	Italy	Steel and Strip
20MnB5	UNI	Italy	Steel and Strip
1.553	BS	British	Steel and Strip
20MnB5	BS	British	Steel and Strip

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com