

Material: EN 1982 CC751S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.100 max.	As-Cast	
Iron	Fe %	0.250 - 0.500		
Manganese	Mn %	0.150 max.		
Nickel	Ni %	0.800 max.		
Lead	Pb %	0.800 - 2.200		
Antimony	Sb %	0.050 max.		
Silicon	Si %	0.650 - 1.100		
Tin	Sn %	0.800 max.		
Cu + Ni	Cu%+Ni%	63.500 - 66.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 470 min. Yield Strength in Mpa 310 min. Elongation in % 3 min. Reduction of Area in % - Hardness in HB 150 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB751S	BS	British	Ingot and Casting
CC751S	DIN	Germany	Ingot and Casting
CC751S	UNI	Italy	Ingot and Casting
CC751S	BS	British	Ingot and Casting
CC751S	ONORM	Australia	Ingot and Casting
CC751S	AFNOR NF	France	Ingot and Casting
CC751S	CSN	Czech Republic	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com