

Material: EN 1982 CuSn3Zn8Pb5-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.500 max.		
Nickel	Ni %	2.000 max.		
Phosphorus	P %	0.030 max.		
Lead	Pb %	3.500 - 5.800		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.250 max.		
Silicon	Si %	0.010 max.		
Tin	Sn %	2.200 - 3.500	Mechanical Properties	
Zinc	Zn %	7.500 - 10.000	Tensile Strength in Mpa	180 - 220
Cu + Ni	Cu%+Ni%	81.000 - 85.500	Yield Strength in Mpa	85 - 100
-	-	-	Elongation in %	12 - 15
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	60 - 70
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC490K	BS	British	Ingot and Casting
CB490K	DIN	Germany	Ingot and Casting
CuSn3Zn8Pb5-B	DIN	Germany	Ingot and Casting
CB490K	EN	European Union	Ingot and Casting
CB490K	AFNOR NF	France	Ingot and Casting
CuSn3Zn8Pb5-B	AFNOR NF	France	Ingot and Casting
CB490K	UNI	Italy	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com