

Material: EN 1982 CuZn38Al-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.100 - 0.800	As-Cast	
Iron	Fe %	0.400 max.		
Manganese	Mn %	0.400 max.		
Nickel	Ni %	0.800 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	0.100 max.		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.100 max.		
Cu + Ni	Cu%+Ni%	59.000 - 64.000	Mechanical Properties	
Zinc	Zn %	Balance	Tensile Strength in Mpa	380 min.
-	-	-	Yield Strength in Mpa	130 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	75 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC767S	BS	British	Ingot and Casting
CB767S	UNI	Italy	Ingot and Casting
CB767S	MSZ	Hungary	Ingot and Casting
CB767S	DIN	Germany	Ingot and Casting
CB767S	AFNOR NF	France	Ingot and Casting
CuZn38Al-B	ONORM	Australia	Ingot and Casting
CuZn38Al-B	MSZ	Hungary	Ingot and Casting

Disclaimer: **All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.**

Customer Care: +91-99090 45075 Email: info@icastllp.com