

Material: EN X 8 CrNiMoVNb 16 13

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: EN X 8 CrNiMoVNb 16 13 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Flat

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.100	Solution Annealing	
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	15.500 - 17.500		
Molybdenum	Mo %	1.100 - 1.500		
Nickel	Ni %	12.500 - 14.500		
Vanadium	V %	0.600 - 0.850		
Niobium	Nb %	1.200 max.		
Nitrogen	N %	0.060 - 0.140	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	540 - 740
-	-	-	Yield Strength in Mpa	255 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4988	BS	British	Tube
1.4988	DIN	Germany	Steel
1.4988	EN	European Union	Steel
X8CrNiMoVNb16 13	DIN	Germany	Steel and Tube
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com