

Material: GOST CuZn39Pb3

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: GOST CuZn39Pb3 Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.050 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.300 max.		
Nickel	Ni %	0.300 max.		
Lead	Pb %	2.500 - 3.500		
Tin	Sn %	0.300 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	57.000 - 59.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	360 min.
-	-	-	Yield Strength in Mpa	150 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	90 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn39Pb3	DIN	Germany	Rod
LS58-3	GOST	Russia	Rod
CuZn39Pb3	ISO	International	Rod
CU 3	ISO	International	Rod
C 3604 BD	JIS	Japan	Rod
C 3604 BE	JIS	Japan	Rod
C 3604 BF	JIS	Japan	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com