

Material: IS 1458 Class V

Standard Specification for Railway Bronze Ingots and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: IS 1458 Railway Bronze Ingots and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingots and Casting

Chemical Composition		
Tin	Sn %	4.000 - 6.000
Lead	Pb %	4.000 - 6.000
Zinc	Zn %	4.000 - 6.000
Phosphorus	P %	0.050 max.
Iron	Fe %	0.300 max.
Antimony	Sb %	0.300 max.
Iron + Antimony	Fe% + Sb%	0.500 max.
Aluminium	Al %	0.010 max.
Other	Ot%	0.600 max.
Copper	Cu %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	186 min.
Yield Strength in Mpa	-
Elongation in %	8 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India