

# Material: IS 1545 CuZn29Sn1As-TA

## Standard Specification for Solid drawn Copper and Copper Alloy Tubes for Condenser and Heat Exchangers

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** IS 1545 Solid drawn Copper and Copper Alloy Tubes for Condenser and Heat Exchangers

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Tube

Chemical Composition		
Arsenic	As %	0.020 - 0.060
Iron	Fe %	0.060 max.
Nickel	Ni %	0.100 max.
Other	Ot%	0.300 max.
Lead	Pb %	0.070 max.
Tin	Sn %	0.900 - 1.500
Copper	Cu %	70.000 - 73.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Drawn or Annealing or Half Hardening or Tempering & Annealing or Annealing

Mechanical Properties	
Tensile Strength in Mpa	340 min.
Yield Strength in Mpa	-
Elongation in %	55 min.
Reduction of Area in %	-
Hardness in HV	80 - 150
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn29Sn1As	IS	India	Tube
CuZn29Sn1As-HD	IS	India	Tube
CuZn29Sn1As-O	IS	India	Tube
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India