

Material: IS 4413 CuZn30

Standard Specification for Brass Wires for General Engineering Purposes

Group: Non-Ferrous Copper Alloy

Sub Group: IS 4413 Brass Wires for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Wire

Chemical Composition			Heat Treatment	
Lead	Pb %	0.050 max.	Annealing or Half Hardening or Hardening	
Iron	Fe %	0.050 max.		
Other	Ot%	0.300 max.		
Copper	Cu %	68.500 - 71.500		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	315 min.
			Yield Strength in Mpa	-
			Elongation in %	45 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn37	IS	India	Strip and Foil
CZ 106	BS	British	Sheet, Strip and Foil
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com