

Material: IS 6912 Cu FNS

Standard Specification for Copper and Copper Alloy Forging Stock and Forgings

Group: Non-Ferrous Copper Alloy

Sub Group: IS 6912 Copper and Copper Alloy Forging Stock and Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Forging

Chemical Composition			Heat Treatment	
Lead	Pb %	1.000 - 2.500	As Raw	
Iron	Fe %	0.300 max.		
Manganese	Mn %	0.200 - 0.300		
Nickel	Ni %	9.000 - 11.000		
Copper	Cu %	44.000 - 48.000		
Other	Ot%	0.500 max.		
Copper	Cu %	44.000 - 48.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	460 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com