

Material: IS 8500 Fe440B

Standard Specification for Structural Steel - MiCroalloyed

Group: Ferrous Mild Steel Alloys

Sub Group: IS 8500 Fe440B Structural Steel - MiCroalloyed

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Plate and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.	As Raw or Normalizing	
Silicon	Si %	0.450 max.		
Manganese	Mn %	1.300 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Cerium	Ce %	0.400 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 440 min. Yield Strength in Mpa 300 min. Elongation in % 22 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 50 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Fe440	IS	India	Plate and Bar
2062 E 350	IS	India	Steel, Plate, Wire, Rod, Tube and Forging
1018	SAE	USA	Steel, Plate, Wire, Rod, Tube and Forging
1018	AISI	USA	Steel, Plate, Wire, Rod, Tube and Forging
A 830 G10180	ASTM	USA	Steel, Plate, Wire, Rod, Tube and Forging
G10180	UNS	USA	Steel, Bar, Wire, Rod, Tube and Forging
SA-29 1018	ASME	USA	Steel, Plate, Wire, Rod, Tube and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com