

Material: ISO 301 ZL3

Specification Standards for Zinc alloy ingots intended for castings

Group: Non-Ferrous Zinc Alloy

Sub Group: ISO 301 Zinc alloy ingots intended for castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.900 - 4.300	As-Cast or Aging	
Cadmium	Cd %	0.003 max.		
Copper	Cu %	0.100 max.		
Iron	Fe %	0.035 max.		
Magnesium	Mg %	0.030 - 0.060		
Lead	Pb %	0.004 max.		
Tin	Sn %	0.0015 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 285 min. Yield Strength in Mpa - Elongation in % 10 min. Reduction of Area in % - Hardness in HB 82 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Zamak 2	ANSI/AA	USA	Casting
ZDC 2	JIS	Japan	Casting
ZDC 2	KS	Korea	Casting
B240 AG40A	ASTM	USA	Casting
B240 Zamak 3	ASTM	USA	Casting
GD-ZnAl4	DIN	Germany	Casting
903	SAE	USA	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India