

Material: ISO 4382 CuPb10Sn10

Standard Specification for Cast Copper Alloys

Group: Non-Ferrous Copper Alloy

Sub Group: ISO 4382 Cast Copper Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.250 max.		
Manganese	Mn %	0.200 max.		
Nickel	Ni %	2.000 max.		
Phosphorus	P %	0.100 max.		
Lead	Pb %	8.000 - 11.000		
Sulphur	S %	0.100 max.		
Antimony	Sb %	0.500 max.		
Silicon	Si %	0.010 max.		
Tin	Sn %	9.000 - 11.000		
Zinc	Zn %	2.000 max.	Mechanical Properties	
Copper	Cu %	Balance	Tensile Strength in Mpa	180 - 220
-	-	-	Yield Strength in Mpa	80 - 140
-	-	-	Elongation in %	3 - 7
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	65 - 70
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LB2	BS	British	Casting
937B	AS	Australia	Ingot and Casting
C93700	AS	Australia	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com