

Material: ISO NiCr 15 Fe 7 TiAl

Standard Specification for Nickel and Nickel-Related Alloys

Group: Non-Ferrous Nickel Alloys

Sub Group: ISO NiCr 15 Fe 7 TiAl Nickel and Nickel-Related Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Round Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 - 0.100	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	14.000 - 17.000		
Aluminium	Al %	1.100 - 1.350		
Sulphur	S %	0.015 max.		
Molybdenum	Mo %	0.500 max.		
Nb + Ta	Nb% + Ta%	0.700 - 1.200		
Iron	Fe %	5.000 - 9.000		
Titanium	Ti %	2.000 - 2.600		
Nickel	Ni %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	1100 - 1300
-	-	-	Yield Strength in Mpa	750 max.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	20 min.
-	-	-	Hardness in HRC	32 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel 751	SAE	USA	Round Bar
N07751	UNS	USA	Round Bar
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com