

Material: JIS C 3601 W

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: JIS C 3601 W Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.	As Raw or Solution Heat Treated	
Lead	Pb %	1.800 - 3.700		
Fe + Sn	Fe% + Sn%	0.500 max.		
Copper	Cu %	59.000 - 63.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	295 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn36Pb3	DIN	Germany	Rod
MO61	PN	Poland	Rod
CZ 124	BS	British	Rod
C 3601 BD	JIS	Japan	Rod
C 3602 BD	JIS	Japan	Rod
C 3602 BE	JIS	Japan	Rod
C 3602 BF	JIS	Japan	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com