

Material: JIS C 3605 BE

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: JIS C 3605 BE Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Arsenic	As %	0.020 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.500 max.		
Lead	Pb %	3.500 - 4.500		
Fe + Sn	Fe% + Sn%	0.800 max.		
Nickel	Ni %	0.200 max.		
Copper	Cu %	56.000 - 60.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 335 min. Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in HV 80 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn38Pb4	DIN	Germany	Rod
C 3604 W	JIS	Japan	Rod
C 3605 BD	JIS	Japan	Rod
CuZn38Pb4	EN	European Union	Rod
CW609N	EN	European Union	Rod
CuZn38Pb4	AFNOR NF	France	Rod
CW609N	AFNOR NF	France	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com