

Material: JIS FCD 400-18

Standard Specification For Spheoidal Graphiite Cast Irons Castings

Group: Ferrous SG Iron I Ductile Iron Alloys

Sub Group: JIS FCD 400-18 Spheoidal Graphiite Cast Irons Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	-	As-Cast	
Silicon	Si %	-		
Manganese	Mn %	-		
Phosphorus	P %	-		
Sulphur	S %	-		
Chromium	Cr %	-		
Nickel	Ni %	-		
Copper	Cu %	-		
Iron	Fe %	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	400 min.
-	-	-	Yield Strength in Mpa	250 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	130 - 180
-	-	-	Impact in Joule	14 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
JS 400-18-LT	ISO	International	Casting
JS 400-18-LT	AS	Australia	Casting
EN-GJS-400-18-LT	AFNOR NF	France	Casting
EN-JS1025	DIN	Germany	Casting
5.3103	EN	European Union	Casting
EN-GJS-400-18-LT	NS	Norway	Casting
EN-JS1025	BS	British	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India