

Material: JIS G 3539 SWCH 12A

Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

Group: Ferrous Mild Steel Alloys

Sub Group: JIS G 3539 SWCH 12A Carbon Steel Wire Rods for Cold Heading and Cold Forging

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Wire Rod and Forging

Chemical Composition		
Carbon	C %	0.100 - 0.150
Silicon	Si %	0.100 max.
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Aluminium	Al %	0.020 min.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Normalizing or Annealing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	340 min.
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	45 min.
Hardness in HRC	90 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SWRCH 12A	JIS	Japan	Wire Rod and Forging
SWRCH12A	MS	Malaysia	Wire Rod and Forging
SWRCH12A	KS	Korea	Wire Rod and Forging
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India