

Material: JIS G 3539 SWCH 12R

Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

Group: Ferrous Mild Steel Alloys

Sub Group: JIS G 3539 SWCH 12R Carbon Steel Wire Rods for Cold Heading and Cold Forging

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Wire Rod and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.150	As Raw or Normalizing or Annealing or Hardening and Tempering	
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 340 min. Yield Strength in Mpa - Elongation in % 45 min. Reduction of Area in % - Hardness in HRC 90 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SWRCH 12R	JIS	Japan	Wire Rod and Forging
SWRM 12	KS	Korea	Wire Rod and Forging
SWRMF12	KS	Korea	Wire Rod and Forging
SWRCH12R	KS	Korea	Wire Rod and Forging
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com