

Material: JIS H 5301 ZDC 2

Specification Standards for Die Castings

Group: Non-Ferrous Zinc Alloy

Sub Group: JIS H 5301 Die Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.500 - 4.300	As-Cast or Aging	
Cadmium	Cd %	0.004 max.		
Copper	Cu %	0.250 max.		
Iron	Fe %	0.100 max.		
Magnesium	Mg %	0.020 - 0.060		
Lead	Pb %	0.005 max.		
Tin	Sn %	0.003 max.		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 285 min. Yield Strength in Mpa - Elongation in % 10 min. Reduction of Area in % - Hardness in HB 82 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Zamak 2	ANSI/AA	USA	Casting
ZDC 2	KS	Korea	Casting
B240 AG40A	ASTM	USA	Casting
B240 Zamak 3	ASTM	USA	Casting
GD-ZnAl4	DIN	Germany	Casting
ZL3	ISO	International	Casting
903	SAE	USA	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com