

Material: JIS SCPH 32-CF

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: JIS SCPH 32-CF Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	1.900 - 2.600		
Molybdenum	Mo %	0.900 - 1.200		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.500 max.		
Tungsten	W %	0.100 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 410 min. Yield Strength in Mpa 205 min. Elongation in % 19 min. Reduction of Area in % - Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G17CrMo9-10	BS	British	Plate, Tubes and Forging
G17CrMo9-10	ISO	International	Casting
1.7379	ISO	International	Casting
15 CD9.10-M	AFNOR NF	France	Pump, Valve and Fitting
SCPH 32	JIS	Japan	Casting
A 217 Grade WC9	ASTM	USA	Casting
A 217 J21890	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com