

Material: JIS SCPL 31

Standard Specification for Low alloy steel castings for low temperature and high pressure service

Group: Ferrous Mild Steel Alloys

Sub Group: JIS SCPL 31 Low Alloy Steel Castings for Low Temperature and High Pressure Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.350 max.		
Nickel	Ni %	3.000 - 4.000		
Copper	Cu %	0.500 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	480 min.
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	21 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
BL2	BS	British	Casting
GS-10 Ni 14	DIN	Germany	Casting
G 9 Ni 14	EN	European Union	Casting
Ao 10 Ni 14	MSZ	Hungary	Casting
G9Ni14	UNI	Italy	Steel
J31550	UNS	USA	Casting
A757 B2N B2Q	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com