

Material: KS D6724 MB3

Standard Specification for Magnesium Alloy Bars

Group: Non-Ferrous Magnesium Alloy

Sub Group: KS D6724 Magnesium Alloy Bars

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Bar

Chemical Composition			Heat Treatment	
Aluminium	Al %	7.800 - 9.200	As-Cast or Solution Treated or Fully Treated	
Copper	Cu %	0.050 max.		
Iron	Fe %	0.005 max.		
Manganese	Mn %	0.120 - 0.400		
Nickel	Ni %	0.005 max.		
Other	Ot%	0.300 max.		
Silicon	Si %	0.100 max.		
Zinc	Zn %	0.200 - 0.800		
Magnesium	Mg %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 290 - 330 Yield Strength in Mpa 185 - 230 Elongation in % 2 - 10 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Mg-Al8Zn	ISO	International	Bar and Wire
MBD-AZ80	JIS	Japan	Bar and Wire
MS-AZ80	JIS	Japan	Shape
MWD-AZ80	JIS	Japan	Bar and Wire
B107 AZ80A	ASTM	USA	Bar, Rod, Tube and Wire
B951 AZ80A	ASTM	USA	Bar and Wire
MgAl8Zn	DIN	Germany	Bar and Wire

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com