

Material: MSZ 40 NiCrSi 35-25

Standard Specification for Heat Resisting Steel Castings

Group: Ferrous Stainless Steel Alloys

Sub Group: MSZ 40 NiCrSi 35-25 Heat Resisting Steel Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.500	As - Cast	
Silicon	Si %	1.000 - 2.500		
Manganese	Mn %	0.500 - 1.500		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	33.000 - 36.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4857	DIN	Germany	Casting
G X 40 NiCrSi 35-25	UNS	USA	Casting
N08705	UNS	USA	Casting
G X 50 NiCrSi 35-25	UNI	Italy	Casting
SCH 24	JIS	Japan	Casting
A297 Grade HP	ASTM	USA	Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com