

Material: MSZ AH 60

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: MSZ AH 60 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.150 - 0.400		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	0.300 max.		
Nickel	Ni %	1.500 - 2.200		
Vanadium	V %	0.050 - 0.150		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
24 Ni 8	DIN	Germany	Steel
G 9 Ni 10	EN	European Union	Casting
SCPL 21	JIS	Japan	Casting
G9Ni10	UNS	USA	Casting
J22501	MSZ	Hungary	Casting
A757 B2N B2Q	ASTM	USA	Casting
20 N 8	AFNOR NF	France	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com