

Material: MSZ Cr 2 Z

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: MSZ Cr 2 Z Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.340 - 0.410	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.900 - 1.200		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 750 - 900 Yield Strength in Mpa 510 min. Elongation in % 14 - 40 Reduction of Area in % - Hardness in BHN As Per HT Impact in Joule 35 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
37Cr4	EN	European Union	Bar and Rod
1.7034	EN	European Union	Bar and Rod
37CrS4	EN	European Union	Bar and Rod
1.7038	EN	European Union	Bar and Rod
34 Cr 4 E	ISO	International	Bar and Rod
34 Cr 4 E	JIS	Japan	Bar and Rod
F.1201	UNE	Spain	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com