

# Material: MSZ EN 1982 CC755S

## Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** MSZ EN 1982 Copper and Copper Alloys - Ingots and Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Ingot and Casting

| Chemical Composition |      |                 | Heat Treatment                                                                                                                                                                                             |  |
|----------------------|------|-----------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|
| Aluminium            | Al % | 0.400 - 0.700   | As-Cast                                                                                                                                                                                                    |  |
| Iron                 | Fe % | 0.050 - 0.200   |                                                                                                                                                                                                            |  |
| Manganese            | Mn % | 0.050 max.      |                                                                                                                                                                                                            |  |
| Nickel               | Ni % | 0.200 max.      |                                                                                                                                                                                                            |  |
| Lead                 | Pb % | 1.200 - 1.700   |                                                                                                                                                                                                            |  |
| Silicon              | Si % | 0.050 max.      |                                                                                                                                                                                                            |  |
| Tin                  | Sn % | 0.300 max.      |                                                                                                                                                                                                            |  |
| Copper               | Cu % | 59.500 - 61.000 |                                                                                                                                                                                                            |  |
| Zinc                 | Zn % | Balance         |                                                                                                                                                                                                            |  |
| -                    | -    | -               | <b>Mechanical Properties</b><br>Tensile Strength in Mpa 310 - 350<br>Yield Strength in Mpa 180 - 210<br>Elongation in % 3 - 13<br>Reduction of Area in % -<br>Hardness in HB 90 - 100<br>Impact in Joule - |  |
| -                    | -    | -               |                                                                                                                                                                                                            |  |
| -                    | -    | -               |                                                                                                                                                                                                            |  |
| -                    | -    | -               |                                                                                                                                                                                                            |  |
| -                    | -    | -               |                                                                                                                                                                                                            |  |
| -                    | -    | -               |                                                                                                                                                                                                            |  |
| -                    | -    | -               |                                                                                                                                                                                                            |  |

| Cross Reference Table |          |                |                              |
|-----------------------|----------|----------------|------------------------------|
| Material              | Standard | Country        | Grade Belong to the Industry |
| CB755S                | BS       | British        | Ingot and Casting            |
| CC755S                | DIN      | Germany        | Ingot and Casting            |
| CC755S                | UNI      | Italy          | Ingot and Casting            |
| CC755S                | AFNOR NF | France         | Ingot and Casting            |
| CuZn39Pb1AIB-C        | UNE      | Spain          | Ingot and Casting            |
| CuZn39Pb1AIB-C        | CSN      | Czech Republic | Ingot and Casting            |
| CuZn39Pb1AIB-C        | MSZ      | Hungary        | Ingot and Casting            |

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)