

Material: MSZ EN 1982 CuZn35Mn2Al1Fe1-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: MSZ EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.700 - 2.200	As-Cast	
Iron	Fe %	0.500 - 1.800		
Manganese	Mn %	0.500 - 2.500		
Nickel	Ni %	6.000 max.		
Phosphorus	P %	0.020 max.		
Lead	Pb %	0.500 max.		
Antimony	Sb %	0.080 max.		
Silicon	Si %	0.100 max.		
Tin	Sn %	0.800 max.		
Cu + Ni	Cu%+Ni%	56.000 - 64.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 450 - 500 Yield Strength in Mpa 170 - 200 Elongation in % 18 - 20 Reduction of Area in % - Hardness in HB 110 - 120 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC765S	BS	British	Ingot and Casting
CB765S	DIN	Germany	Ingot and Casting
CB765S	BDS	Bulgaria	Ingot and Casting
CB765S	CSN	Czech Republic	Ingot and Casting
CuZn35Mn2Al1Fe1-B	AFNOR NF	France	Ingot and Casting
CuZn35Mn2Al1Fe1-B	ONORM	Australia	Ingot and Casting
CuZn35Mn2Al1Fe1-B	UNE	Spain	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com