

Material: NBN G 9 Ni 10

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: NBN G 9 Ni 10 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.120	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Nickel	Ni %	2.000 - 3.000		
Molybdenum	Mo %	0.200 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 480 - 630 Yield Strength in Mpa 280 min. Elongation in % 24 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G9Ni10	BS	British	Plate, Tubes and Forging
A 352 Grade LC2	ASTM	USA	Casting
A 352 J22500	ASTM	USA	Casting
G 9 Ni 10	BDS	Bulgaria	Casting
G 9 Ni 10	CSN	Czech Republic	Casting
G 9 Ni 10	EN	European Union	Casting
G 9 Ni 10	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com