

Material: NBN GX120Mn13

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: NBN GX120Mn13 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	1.050 - 1.350	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.300 - 0.900		
Manganese	Mn %	11.000 - 14.000		
Phosphorus	P %	0.060 max.		
Sulphur	S %	0.045 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN 300 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
BW10	BS	British	Casting
Z 120 M 12 M	AFNOR NF	France	Casting
1.3401	DIN	Germany	Casting
1.3802	ONORM	Australia	Casting
1.3802	NBN	Belgium	Casting
1.3802	BDS	Bulgaria	Casting
GX120Mn13	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com