

Material: NMX CW-12M

Standard Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

Group: Non-Ferrous Nickel Alloys

Sub Group: NMX CW-12M Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.120 max.
Silicon	Si %	1.500 max.
Manganese	Mn %	1.000 max.
Chromium	Cr %	15.500 - 20.000
Iron	Fe %	7.500 max.
Molybdenum	Mo %	16.000 - 20.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Cobalt	Co %	2.500 max.
Vanadium	V %	0.400 max.
Tungsten	W %	5.250 max.
Nickel	Ni %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
As-Cast or Annealing or Age Hardning	

Mechanical Properties	
Tensile Strength in Mpa	495 min.
Yield Strength in Mpa	315 min.
Elongation in %	4 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10774 Grade 13	IS	India	Casting
A 743 Grade CW-12M	ASTM	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India