

Material: ONORM 1.7185

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: ONORM 1.7185 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.360	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	1.200 - 1.500		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.300 - 0.600		
Boron	B %	0.0008 - 0.0050		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	900 - 1300
-	-	-	Yield Strength in Mpa	750 min.
-	-	-	Elongation in %	13 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardness in BHN	255 max.
-	-	-	Impact in Joule	50 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
33MnCrB5-2	EN	European Union	Bar and Rod
1.7185	EN	European Union	Bar and Rod
33MnCrB5-2	ISO	International	Bar and Rod
33MnCrB5-2	ONORM	Australia	Bar and Rod
1.7185	NBN	Belgium	Bar and Rod
33MnCrB5-2	NBN	Belgium	Bar and Rod
1.7185	SFS	Finland	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com