

Material: ONORM GX25CrNiSi18-9

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: ONORM GX25CrNiSi18-9 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.350	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.500 - 2.500		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Molybdenum	Mo %	0.500 max.		
Cobalt	Co %	1.000 max.		
Copper	Cu %	0.250 max.		
Niobium	Nb %	0.600 max.		
			Mechanical Properties	
Vanadium	V %	0.120 max.	Tensile Strength in Mpa	450 min.
Tungsten	W %	0.600 max.	Yield Strength in Mpa	230 min.
Iron	Fe %	Balance	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
302C35	BS	British	Casting
Z 25CN20.10-M	AFNOR NF	France	Casting
1.4825	ONORM	Australia	Casting
GX25CrNiSi18-9	BS	British	Casting
1.4825	EN	European Union	Casting
GX25CrNiSi18-9	EN	European Union	Casting
1.4825	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com