

Material: PN CuSn4Te1P

Standard Specification for Copper-Tin Alloy Rod

Group: Non Ferrous Copper Alloys

Sub Group: PN CuSn4Te1P Copper-Tin Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	As Raw or Solution Heat Treated	
Nickel	Ni %	0.200 max.		
Phosphorus	P %	0.100 - 0.400		
Tellurium	Te %	0.500 - 1.000		
Tin	Sn %	4.000 - 5.000		
Zinc	Zn %	0.300 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.
-	-	-	Yield Strength in Mpa	300 - 400
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	160 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuSn4Te1P	DIN	Germany	Rod
CuSn4Te1P	BS	British	Rod
CW457K	BS	British	Rod
CuSn4Te1P	SS	Sweden	Rod
CW457K	SS	Sweden	Rod
CW457K	PN	Poland	Rod
CuSn4Te1P	UNE	Spain	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com