

Material: PN MI

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: PN MI Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition		
Arsenic	As %	0.010 max.
Sulphur	S %	0.200 - 0.600
Bismuth	Bi %	0.002 max.
Iron	Fe %	0.050 max.
Nickel	Ni %	0.200 max.
Other	Ot %	0.300 max.
Antimony	Sb %	0.005 max.
Tin	Sn %	0.050 max.
Copper	Cu %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Solution Heat Treated	

Mechanical Properties	
Tensile Strength in Mpa	250 min.
Yield Strength in Mpa	150 - 240
Elongation in %	8 min.
Reduction of Area in %	-
Hardness in BHN	85 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuSP	DIN	Germany	Rod
2.1525	DIN	Germany	Rod
CuSi 3 Mn	DIN	Germany	Rod
SB-Cu	DIN	Germany	Rod
CuS	PN	Poland	Rod
CuSP	BS	British	Rod
CW114C	BS	British	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India