

Material: SAE 1084

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group: Ferrous Mild Steel Alloys

Sub Group: SAE 1084 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.800 - 0.930	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Boron	B %	0.0005 - 0.003		
Chromium	Cr %	0.150 max.		
Copper	Cu %	0.200 min.		
Molybdenum	Mo %	0.060 max.		
Nickel	Ni %	0.200 max.		
Lead	Pb %	0.15 - 0.350		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 690 - 820 Yield Strength in Mpa 450 min. Elongation in % 10 min. Reduction of Area in % 25 - 40 Hardness in HB 192 - 241 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10840	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1084	AISI	USA	Steel and Bar
A 1040 1084	ASTM	USA	Steel
A 29 1084	ASTM	USA	Steel and Bar
A 510 1084	ASTM	USA	Wire Rods, Round Wire and Steel
A 576 10L84	ASTM	USA	Steel and Bar
A 713 G10840	ASTM	USA	Steel and Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com