

Material: SAE 1522

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Bars, Wire Rod and Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: SAE 1522 Carbon Steel Compositions For Forging To Hot-Rolled Bars, Wire Rod and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rod and Tubing

Chemical Composition		
Carbon	C %	0.180 - 0.240
Manganese	Mn %	1.100 - 1.140
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Boron	B %	0.0005 - 0.003
Chromium	Cr %	0.150 max.
Copper	Cu %	0.200 max.
Molybdenum	Mo %	0.060 max.
Nickel	Ni %	0.200 max.
Lead	Pb %	0.150 - 0.350
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Annealing or Normalizing or Hardening and Tempering	

Mechanical Properties	
Tensile Strength in Mpa	410 min.
Yield Strength in Mpa	340 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15220	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1522	AISI	USA	Steel and Bar
A 29 1522	ASTM	USA	Steel and Bar
A 510 1522	ASTM	USA	Wire Rods, Round Wire and Steel
A 576 15L22	ASTM	USA	Steel and Bar
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India