

## Material: SAE 1524

### Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** SAE 1524 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Steel

Chemical Composition		
Carbon	C %	0.190 - 0.250
Manganese	Mn %	1.350 - 1.650
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Boron	B %	0.0005 - 0.003
Chromium	Cr %	0.150 max.
Copper	Cu %	0.200 max.
Molybdenum	Mo %	0.060 max.
Nickel	Ni %	0.200 max.
Lead	Pb %	0.150 - 1.650
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Annealing or Normalizing or Hardening and Tempering	

Mechanical Properties	
Tensile Strength in Mpa	510 - 570
Yield Strength in Mpa	280 min.
Elongation in %	12 min.
Reduction of Area in %	35 - 42
Hardness in HB	149 - 163
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15240	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1524	AISI	USA	Steel and Bar
A 29 1524	ASTM	USA	Steel and Bar
A 510 1524	ASTM	USA	Wire Rod, Round Wire and Steel
A 830 G15240	ASTM	USA	Plate and Steel
A 513 Grade 1524	ASTM	USA	Tubing
A 519 1524	ASTM	USA	Tubing

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India