

Material: SAE 2024

Standard Specification For Aerospace Material Aluminium Alloy

Group: Non-Ferrous Aluminium Alloys

Sub Group: SAE 2024 Aerospace Material Aluminium Alloy

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Plate and Sheet

Chemical Composition			Heat Treatment	
Silicon	Si %	0.500 max.	As Raw or Temper or Solution Treated or Aging	
Chromium	Cr %	0.100 max.		
Manganese	Mn %	0.300 - 0.900		
Magnesium	Mg %	1.200 - 1.800		
Copper	Cu %	3.800 - 4.900		
Iron	Fe %	0.500 max.		
Zinc	Zn %	0.250 max.		
Titanium	Ti %	0.150 max.		
Other	Ot %	1.000 max.		
Aluminium	Al %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	200 min.
-	-	-	Yield Strength in Mpa	97 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2024	AS	Australia	Plate and Sheet
2024A	AS	Australia	Plate and Sheet
2024	NBN	Belgium	Bar
AlCuMg2	ONORM	Australia	Plate and Sheet
AL-P2024	ONORM	Australia	Sheet and Strip
EN AW-2024	NBN	Belgium	Bar and Tube
EN AW-Al Cu4Mg1	NBN	Belgium	Bar and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com