

Material: SAE 5819

Standard Specification for Cobalt-Based alloy, Wire

Group: Non-Ferrous Cobalt Alloys

Sub Group: SAE 5819 Cobalt-Based alloy, Wire

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.300	As-Cast or Annealing	
Silicon	Si %	1.000 max.		
Chromium	Cr %	25.000 - 29.000		
Nickel	Ni %	2.000 - 3.750		
Molybdenum	Mo %	5.000 - 6.000		
Iron	Fe %	3.000 max.		
Boron	B %	0.006 max.		
Phosphorus	P %	0.020 max.		
Manganese	Mn %	1.000 max.		
Sulphur	S %	0.020 max.		
Cobalt	Co %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	34 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Stellite 21	Gravity	India	Casting
5385	SAE	USA	Casting
ERCCoCr-E	ASME	USA	Casting
ERCoCr-E	ASME	USA	Casting
R30021	UNS	USA	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com